

Office Action Response
U.S.S.N. 10/073,682
Page No. 2 of 18

IN THE CLAIMS:

Please amend the claims as shown in the following claim listing.

CLAIM LISTING:

1. (Original) An ultra-high molecular weight polyethylene film:
having a tensile strength from between about 0.7 GPa and about 5 GPa where said
polyethylene has an intrinsic viscosity from between about 5 and about 50 db/g;
that is stretched, fibrillated and slit into a micromesh tape suitable for use as an
interproximal device having:
 - a fibrillation density from between about 5% and about 90% of the total tape
surface,
 - a width from between about 0.035 and about 0.12 inches,
 - a thickness from between about 0.001 and about 0.004 inches, and
 - a denier from between about 200 and about 600;wherein said micromesh interproximal device is coated with an oral care
substance at from between about 10 and about 120 mg/yd and which, during flossing,
releases substantial amounts of said coating while demonstrating ultra shred resistance
and an entrapment factor of at least about two.
2. (Currently Amended) The ultra-high molecular weight polyethylene film
according to Claim 1, wherein said stretching is achieved by a drawing means, wherein
the total draw ~~ratio~~ ratio is from between about 80- and about 200-fold.
3. (Currently Amended) The ultra-high molecular weight polyethylene film
according to Claim 1, wherein said fibrillating is achieved by fibrillating devices as
illustrated in Figs. 5 and 6 selected from the group consisting of a tapping screw-like
fibrillator and a file-like fibrillator.

MAR 02 2005

Office Action Response
U.S.S.N. 10/073,682
Page No. 3 of 18

4. (Original) The coated ultra-high molecular weight polyethylene micromesh interproximal device according to Claim 1, wherein said coating with an oral care substances, is achieved by a coating means selected from the group consisting of: compression loading, injection loading and contact loading, and combinations thereof.

5. (Original) The coated ultra-high molecular weight polyethylene micromesh interproximal device according to Claim 1, wherein said oral care coating substance is selected from the group consisting of: high melt viscosity mixtures, high melt viscosity emulsions, medium-melt viscosity mixtures, medium melt viscosity emulsions, low melt viscosity mixtures and low melt viscosity emulsions, and combinations thereof.

6. (Currently Amended) The coated ultra-high molecular weight polyethylene micromesh interproximal devices according to Claim 5, wherein said high melt viscosity mixtures and high melt viscosity emulsions are compression loaded into said micromesh at levels from between about 10 and about 120 mg/yd and said high melt viscosity mixtures and emulsions comprise saliva soluble, substantially crystal-free coatings containing oral care substances selected from the group consisting of hedonic agents, cleaners, chemotherapeutic agents, ~~Soft Abrasives™~~ abrasives, and mixtures thereof.

7. (Currently Amended) The coated ultra-high molecular weight polyethylene micromesh interproximal devices according to Claim 5, wherein said medium melt viscosity mixtures and medium melt viscosity emulsions are injection loaded into said micromesh at levels from between about 10 and about 120 mg/yd and said medium melt viscosity mixtures and emulsions comprise coatings selected from the group consisting of:

Office Action Response
U.S.S.N. 10/073,682
Page No. 4 of 18

(a) saliva soluble, substantially crystal-free coatings containing oral care substances selected from the group consisting of hedonic agents, cleaners, chemotherapeutic agents, ~~Soft Abrasives™~~ abrasives, and mixtures thereof[:];

(b) saliva gelling, slowly soluble mixtures containing oral care substances selected from the group consisting of hedonic agents, cleaners, chemotherapeutic agents, Soft Abrasives™ and mixtures thereof; and

mixtures of (a) and (b).

8. (Currently Amended) The coated ultra-high molecular weight polyethylene micromesh interproximal devices according to Claim 5, wherein said low melt viscosity emulsions are contact loaded onto said micromesh at levels from between about 10 and 120 mg/yd and said low melt viscosity mixtures and emulsions comprise coatings selected from the group consisting of:

- (a) saliva soluble coatings
- (b) saliva insoluble coatings, and
- (c) mixtures of (a) and (b).

9. (Original) An ultra-high molecular weight polyethylene micromesh tape suitable for use as an interproximal device, wherein the dispensing means for said tape is selected from the group consisting of bobbin based dispensers and single dose dispensers.

10. (Original) A shred-resistant, ultra-high molecular weight polyethylene, micromesh interproximal device produced by fibrillating stretched

Office Action Response
U.S.S.N. 10/073,682
Page No. 5 of 18

polyethylene tape having a tensile strength from between about 0.7 GPa and about 5 GPa, where said polyethylene has an intrinsic viscosity of from between about 5 and about 50 dl/g; and wherein said device is coated with a saliva-soluble, substantially crystal-free coating at a load from between about 10 and about 120 mg/yd.

11. (Original) A method of manufacturing the micromesh interproximal device of Claim 1, wherein said stretched polyethylene tape is run at a transfer speed from between about 1 and about 1000 m/min and said fibrillating is carried out simultaneously with a rotary fibrillator positioned in fibrillating contact with said polyethylene tape and run at a rotational line speed from between about 10 and about 3000 m/min and said coating is carried out at between about 1 and about 5 yards per second.

12. (Original) A method of manufacturing the micromesh interproximal device of Claim 11, wherein said fibrillated tape is compression loaded by passing said fibrillated tape through a coating chamber and thereafter passing said coated fibrillated tape between juxtapositioned heated rollers under compression conditions.

13. (Original) A micromesh interproximal device according to Claim 5, wherein said oral care coating substance contains cleaners selected from the group consisting of:

sodium lauryl sulfate,
sodium lauryl sarcosinate,
polyethylene glycol stearate,
polyethylene glycol monostearate,
coconut monoglyceride sulfonates,
sodium alkyl sulfate,
sodium alkyl sulfoacetates,

Office Action Response
U.S.S.N. 10/073,682
Page No. 6 of 18

block copolymers of polyoxyethylene and polyoxybutylene,
allylpolyglycol ether carboxylates,
polyethylene derivatives of sorbitan esters,
propoxylated cetyl alcohol,
block copolymers comprising a cogeneric mixture of conjugated polyoxypropylene and
polyoxyethylene compound having as a hydrophobe a polyoxypropylene polymer of at
least 1200 molecular weight,
soap powder,
and mixtures thereof.

14. (Original) A micromesh interproximal device according to Claim 5,
wherein said oral care coating substance contains Formula Modifiers selected from the
group consisting of:

saliva-insoluble formula modifiers, including:

microcrystalline waxes

paraffin wax

carnauba, beeswax and other natural waxes

animal and vegetable fats and oils

low-melt point, orally suitable polymers and copolymers;

saliva-soluble formula modifiers include so-called water soluble waxes, including:

liquid polyethylene glycols

solid polyethylene glycols

liquid polypropylene glycols

solid polypropylene glycols,

triacetin, and

Office Action Response
U.S.S.N. 10/073,682
Page No. 7 of 18

low melt temperature, water-soluble polymers, including:
hydroxyethylcellulose
hydroxypropylcellulose
carboxy derivatives of cellulose and
orally suitable saliva gelling or water-soluble copolymers of various resins.

15. (Currently Amended) A micromesh interproximal device according to Claim 5, wherein said oral care coating substance contains chemotherapeutic ingredients selected from the group consisting of:

anti-tartar substances, an emulsion of polydimethyl siloxane and polyoxypropylene-polyoxyethylene block copolymers MICRODENT®, a high shear mixture of high molecular weight block copolymers of ethylene oxide and propylene oxide with high viscosity polydimethylsiloxane polymers ULTRAMULSION®, tetrasodium pyrophosphate (TSPP), tetrapotassium pyrophosphates, and mixtures thereof;

first generation anti-biofilm agents, oxygenating compounds, quaternary ammonium compounds, phenolic compounds and plant alkaloids selected from the group consisting of:

benzethonium chloride and cetylpyridinium chloride,
thymol and eucalyptol in a mixture of methyl salicylate, benzoic acid and boric acid and phenol,
flavor oils,
sanguinaria extract with zinc chloride, and
triclosan;

Office Action Response
U.S.S.N. 10/073,682
Page No. 8 of 18

- (3) second generation anti-biofilm agents, chlorhexidine, alexidine, octenidine and stannous fluoride;
- (4) desensitizing agents, NSAIDs, antibiotics, anti-thrush agents, anti-caries agents, antimicrobials, COX-2 agents;
- (5) dry mouth relieving agents;
- (6) NSAIDs;
- (7) antibiotics; and

mixtures thereof.

16. (Currently Amended) A micromesh interproximal device according to Claim 5, wherein said oral care coating substance contains ~~Soft Abrasives~~TM abrasives selected from the group consisting of:

dicalcium phosphate (DCP),
pumice,
aluminum silicate,
silica,
glass beads,
titanium oxide,
rice flour,
sodium hexametaphosphate,
quartz,

Office Action Response
U.S.S.N. 10/073,682
Page No. 9 of 18

novaculite,
silicon carbide,
alumina zirconia,
alumina,
polishing alumina,
calcined aluminum oxide,
silicon zirconium oxide, and
mixtures thereof.

17. (Currently Amended) A micromesh interproximal device according to Claim 1, where said micromesh structure is selected from the group of structures illustrated in Figs. 1a through 1f and combinations thereof.


18. (Original) A micromesh interproximal device according to Claim 6, wherein the additive responsible for maintaining said coating substantially crystal-free and free from substantial flaking is an aliphatic long chain, fatty alcohol selected from the group consisting of:

1-decanol	1-heptadecanol	1-pentacosanol
1-undecanol	1-octadecanol	1-hexacosanol
1-dodecanol	1-nonadecanol	1-heptacosanol
1-tetradecanol	1-eicosanol	1-octacosanol
1-pentadecanol	1-heneicosanol	1-nonacosanol
1-hexadecanol	1-tricosanol	1-triacosanol

1-tetracosanol, and mixtures thereof.

Office Action Response
 U.S.S.N. 10/073,682
 Page No. 10 of 18

19. (Original) A micromesh interproximal device according to Claim 6, wherein the additive responsible for maintaining said coating crystal-free is a liquid surfactant having the general formula:



wherein R_1 , R_2 , R_3 , R_4 are H or aliphatic acyl groups having from between 10 and 30 carbon atoms, and the sum of w , x , y , and z is from between 20 and 80.

20. (Original) A method of cleaning interproximal and subgingival areas of the oral cavity comprising regularly flossing with a shred-resistant, ultra-high molecular weight polyethylene micromesh interproximal device produced by fibrillating stretched polyethylene tape having a tensile strength from between about 0.7 GPa and about 5 GPa, where said polyethylene has an intrinsic viscosity of from between about 5 and about 50 dl/g; and wherein said device is coated with an oral care substance at a load from between about 10 and about 120 mg/yd.

21. (Currently Amended) A method for treating interproximal and subgingival areas of the oral cavity with chlorhexidine comprising regularly flossing with a micromesh interproximal device compression loaded with a saliva-soluble, crystal-free coating containing ~~Soft Abrasives™~~ abrasives and between about 0.2 and about 2.0 mg/yd of chlorhexidine.

Office Action Response
U.S.S.N. 10/073,682
Page No. 11 of 18

22. (Currently Amended) A method for treating interproximal and subgingival areas of the oral cavity with stannous fluoride, comprising regularly flossing with a micromesh interproximal device compression loaded with a saliva-soluble, crystal-free coating containing ~~Soft Abrasives~~TM abrasives and between about 1 and about 3 of stannous fluoride.

REMAINDER OF PAGE INTENTIONALLY BLANK